



UNITED STATES ENVIRONMENTAL PROTECTION AGENCY

Drywall Sampling Analysis

Background

Consumers from more than 10 States and the District of Columbia have reported concerns related to drywall imported from China that is in their houses. The Consumer Product Safety Commission (CPSC) is the lead federal agency for this issue. The U.S. Environmental Protection Agency (EPA) is working with CPSC and the Centers for Disease Control and Prevention-Agency for Toxic Substances and Disease Registry (CDC-ATSDR), in coordination with State and local authorities, to investigate this matter.

To gather more information about Chinese drywall, CDC-ATSDR requested that EPA conduct an elemental analysis of Chinese drywall and compare it with drywall manufactured in the United States.

Analysis of Drywall Samples

With CDC-ATSDR's concurrence, two wallboard samples from Florida houses known to have been manufactured in China were selected by the Florida Department of Health (FDOH) for analysis. Additionally, four samples of U.S.-manufactured drywall were purchased by EPA from local stores in Edison, New Jersey and included in the analysis.

Prior to analysis, the thin layer of paint was scraped off of the two Chinese drywall samples for metals analysis. The paper was then separated from the solid (gypsum) material of all six drywall samples and placed into separate glass jars. The paper portions of the samples were analyzed for metals, semi volatile organic compounds (SVOCs) and formaldehyde. The gypsum samples were analyzed for metals, SVOCs, volatile organic compounds (VOCs), formaldehyde, sulfide, water soluble chlorides, total organic carbon (TOC), pH and loss on ignition (LOI).

The results of this analysis will inform additional testing by CPSC to help determine the compounds that may be affecting residents and their houses.

Results

The results of the analysis are noted below. It is important to note that the analysis included a very small sample size, and the results of this testing may not be representative of all drywall products. The analysis was conducted to identify the elemental material contained in the drywall samples and is not itself intended to establish a definitive link between the drywall and the conditions being observed in houses.

- Sulfur was detected at 83 parts per millions (ppm) and 119 ppm in the Chinese drywall samples. Sulfur was not detected in the four US-manufactured drywall samples.
- Strontium was detected at 2,570 ppm and 2,670 ppm in the Chinese drywall samples. Strontium was detected in the US-manufactured drywall at 244 ppm to 1,130 ppm. Total acid soluble sulfides were not detected in any samples.
- Iron concentrations of 1,390 ppm and 1,630 ppm were detected in the Chinese drywall samples and in the range of 841 ppm to 3,210 ppm for the US-manufactured drywall samples. Additional drywall samples will be tested to determine whether the iron is present as oxide, sulfide or sulfate.

EPA's analysis showed the presence of two organic compounds in the Chinese drywall that are associated with acrylic paints: propanoic acid, 2-methyl-, 2,2-dimethyl-1-(2-hydroxy-1-methylethyl) propyl ester at estimated concentrations of 58 ppm and 92 ppm, and propanoic acid, 2-methyl-, 3-hydroxy-2,4,4-trimethylpentyl ester at estimated concentrations of 50 ppm and 84 ppm. These compounds were not detected in the US-manufactured drywall.

EPA will continue to work with its federal and state partners to respond to this issue. EPA also is working with a multi-agency and state technical group to develop an indoor sampling protocol for use by CPSC and states to conduct indoor air testing in houses suspected of containing Chinese drywall. The group's goal is to complete the protocol by June 30, 2009. EPA expects that results from the indoor sampling will be evaluated by CDC-ATSDR for possible health implications.



UNITED STATES ENVIRONMENTAL PROTECTION AGENCY
ENVIRONMENTAL RESPONSE TEAM
Edison, New Jersey 08837

May 7, 2009

Ms. Lynn Wilder
Environmental Health Scientist
Agency for Toxic Substances and Disease Registry
Department of Homeland Security
4770 Buford Highway, NE
Mailstop F-57
Atlanta, GA 30341-3717

Subject: Drywall Sample Analysis

Dear Ms. Wilder,

The Agency for Toxic Substances and Disease Registry (ATSDR) contacted the Environmental Response Team (ERT) of the USEPA Office of Superfund Remediation and Technology Innovation (OSRTI) for analytical assistance with the Chinese-manufactured drywall used in Florida. On March 5, 2009, a teleconference was held with ERT, ATSDR and the Florida Department of Health (FDOH). The FDOH provided background information, including the work that had been previously performed by contractors from Lennar and Knauf (a German company that manufactures drywall in China). ATSDR requested that ERT conduct an independent elemental analysis of the Chinese drywall and compare it with the drywall manufactured in the U.S. With ATSDR's concurrence, six wallboard samples were selected for analysis. Two drywall samples known to have been manufactured in China were extracted by FDOH from affected homes in Florida. Four samples of U.S.-manufactured drywall were purchased from local stores in Edison, New Jersey.

Drywall Sample Analysis

ATSDR requested that the ERT analytical laboratory provide support to analyze drywall samples from China suspected of emitting rotten egg odors and causing copper corrosion (e.g., power switches, appliances) throughout the houses with complaints. The corrosion of copper containing items may lead to releases of chlorofluorocarbons (CFCs) and natural gases, depending on their construction materials. Individuals complaining about the drywall in their homes have also reported health issues such as problems with asthma, respiratory irritation, breathing difficulties, coughing, insomnia, eye irritation and headaches. At this time, FDOH has been unable to determine if these issues are directly linked to the suspect drywall. To date, a relatively low number of

samples have been analyzed, and the emission levels detected from samples tested in the laboratory are far lower than those typically associated with such symptoms.

Two Chinese painted drywall samples extracted from Florida homes by FDOH were shipped to Edison for analysis by USEPA/ERT. ERT purchased four US-manufactured drywall samples from local stores for comparison. First, the thin layer of paint was scraped off of two Chinese drywall samples for metals analysis. The top and bottom layers of paper were separated from the solid (gypsum) material of all six drywall samples and placed into separate glass jars. The paper portions of the samples were analyzed for metals, semi volatile organic compounds (SVOCs) and formaldehyde. The gypsum samples were analyzed for metals, SVOCs, volatile organic compounds (VOCs), formaldehyde, sulfide, water soluble chlorides, total organic carbon (TOC), pH and loss on ignition (LOI). Also, an optical microscopic examination was conducted to determine the presence of fly ash.

The drywall sample manufacturers and product names are as follows: US Gypsum/Hamilton (US); PROROC/Certainteed (US); National Gypsum/Gold Bond (US); GP/Tough Rock (US); Knauf/33928-20055 (China); and MIC/33966-12077 (China). The ERT/REAC analytical methods were modified to analyze these samples, as standard methods were not available in the area of sample digestion/preparation procedures.

Analytical Methods

Semi Volatile Organic Compounds: The gypsum and paper portions of the drywall samples were analyzed using ERT/REAC SOP #1805. A specific weight of sample in grams is extracted with a 1:1 methylene chloride/acetone mix in a Soxtherm extractor. The extract is concentrated, spiked with an internal standard mixture and subsequently analyzed by gas chromatography/mass spectrometry (GC/MS). Target analytes are identified by comparing the measured mass spectra and retention times with those obtained from calibration standards acquired under the same operating conditions used for the samples. Quantitation of each identified target analyte is calculated based on the internal standard method. The method was modified to determine the presence of any non-target compounds via a library search for the purpose of tentative identification. The NIST/EPA/NIH Mass Spectral Library containing more than 100,000 spectra was used. The elemental sulfur was analyzed using the sample extracts by GC/MS using an ERT/REAC modified method.

Volatile Organic Compounds: The two Chinese and one US-manufactured drywall gypsum samples were analyzed using ERT/REAC SOP #1807. A known amount of gypsum is weighed into a 40-milliliter (mL) Teflon®-lined septum vial, 5 mL of commercially available water suitable for VOC analysis is added, and the sealed vial is placed in the auto sampler. An additional 5-mL portion of VOC-free water containing surrogate/internal standards is added by the autosampler. In order to purge the compounds out of the dry wall, the samples were heated for five minutes at 75°C. These samples were then purged with helium for 20 minutes at the same temperature,

desorbed (trapped) onto the trap for four minutes and injected into the GC and detected using a 5975 MSD. The method was modified to determine the presence of any non-target compounds via a library search for the purpose of tentative identification. The NIST/EPA/NIH Mass Spectral Library containing more than 100,000 spectra was used.

Metals: The gypsum samples were first screened using a NITON x-ray fluorescence detector (XRF) to determine the presence of any metals. The XRF will help to ascertain whether additional metals that are not included in the Target Analyte List (TAL) routinely analyzed by the laboratory need to be added. The gypsum, paper and paint samples were analyzed for TAL metals using ERI/REAC SOP #1811, *Determination of Metals by Inductively Coupled Plasma (ICP) Methods*, and SOP #1832, *Determination of Mercury by Cold Vapor Atomic Absorption (CVAA)*. Based on the XRF screening, strontium and sulfur were added to the list of analytes.

Formaldehyde, Sulfide, Total Organic Carbon: Analyses for these compounds were contracted to outside laboratories. Formaldehyde was analyzed by high pressure liquid chromatography (HPLC), ultraviolet detection (UV) in accordance with modified NIOSH Method 2016. For acid soluble sulfides, the gypsum samples were distilled using EPA SW-846 Method 9030B, which separates the sulfides from the matrix by adding sulfuric acid to the sample and heating to 70°C. The sulfide was quantified using an iodometric method. TOC was determined using a carbonaceous analyzer in accordance with EPA Region II SOP #C-88.

Water Soluble Chlorides: A specific weight of sample was mixed with a known volume of water prior to analysis. Samples were analyzed using a five-point calibration curve by a modified ferricyanide spectrophotometric technique, as outlined in the Standard Methods for the Examination of Water and Wastewater, Method 4500-Cl-E.

Loss on Ignition and pH: Loss on ignition data were obtained by weighing a known amount of sample into a crucible and igniting at 750°C using the modified Standard Methods for the Examination of Water and Wastewater, Method 2540G. A 5 percent weight by volume of a gypsum sample in water was prepared and mixed using a magnetic stirrer. The pH of the resulting aqueous solution was measured electrometrically using a calibrated pH meter.

Alkalinity and Sulfate: Alkalinity was performed in accordance with the Standard Methods for the Examination of Water and Wastewater, Method 2320B, that uses an acid titrant to measure the buffering capacity or ability to react with acids to a specific pH. Sulfates were determined using EPA Region II SOP #C-19.

Optical Microscopic Examination: The optical microscopic examination was performed at the ERI-Las Vegas laboratory using an Olympus optical microscope.

Discussion of the Results:

The significant differences between the Chinese drywall and the US-manufactured drywall analysis are as follows:

ERT analysis shows the presence of sulfur at 83 ppm and 119 ppm in the Chinese drywall samples and sulfur not detected in four US-manufactured drywall samples. The metal analysis shows the presence of strontium at 2,570 ppm and 2,670 ppm in the Chinese drywall samples, whereas strontium was detected in the US-manufactured drywall at 244 ppm to 1,130 ppm. The total acid soluble sulfides were not detected in any of the drywalls. Further investigation is critical to determine the presence of strontium as strontium sulfate or strontium sulfide using x-ray diffraction.

Iron concentrations of 1,390 ppm and 1,630 ppm were detected in the Chinese drywall samples and in the range of 841 ppm to 3,210 ppm for the US drywall samples. The highest concentration of iron detected in the National Gypsum/Gold Bond drywall was twice as high as the amount found in the Chinese drywall. An investigation will be done using additional drywall samples to determine whether the iron is present as oxide, sulfide or sulfate.

No evidence of fly ash in the Chinese drywall samples was noted based on the optical microscopic examination.

The ERT/REAC SVOC analysis results show the presence of two organic compounds in the Chinese drywall, as tentatively identified by the mass spectrometry library search for the Chinese drywall. The FDOH has requested that ERT further investigate these compounds. The two compounds were propanoic acid, 2-methyl-, 2,2-dimethyl-1-(2-hydroxy-1-methylethyl) propyl ester (CAS # 74367-33-2) at estimated concentrations of 58 and 92 ppm, and propanoic acid, 2-methyl-, 3-hydroxy-2,4,4-trimethylpentyl ester (CAS # 74367-34-3) at estimated concentrations of 50 and 84 ppm. These compounds were not detected in the US-manufactured drywall. ERT analyzed two samples for VOCs by GC/MS. The analyses confirm the presence of the above two compounds in the Chinese drywall, as tentatively identified by the mass spectrometry library search. ERT is in the process of obtaining standards of propanoic acid, 2-methyl-, 2,2-dimethyl-1-(2-hydroxy-1-methylethyl) propyl ester (CAS # 74367-33-2) and propanoic acid, 2-methyl-, 3-hydroxy-2,4,4-trimethylpentyl ester (CAS # 74367-34-3) to confirm the findings. The literature search reveals that these compounds are found in acrylic paints as reported in the following website:

http://www2.mst.dk/common/Udgivramme/Frame.asp?http://www2.mst.dk/udgiv/publications/2008/978-87-7052-763-7/html/kap02_eng.htm

The summary of analytical results of the six drywall (gypsum, paper, and paint) samples is presented in Summary Table 1. The semi-quantitative XRF data for gypsum


analysis are presented in Table 2. The tentatively identified compounds detected by the GC/MS library search for the SVOC analysis are presented in Table 3 for the gypsum and paper portions of the drywall samples.

Work in Progress

The additional drywall samples to be received from CPSC will be analyzed semi-quantitatively for calcium sulfate, strontium sulfide, strontium sulfate, pyrites and iron oxide by x-ray diffraction. The drywall samples from the United States and China will also be analyzed for VOCs, SVOCs, metals including strontium, sulfide, sulfite, formaldehyde, TOC and LOI. An optical microscopic examination for fly ash will also be conducted. Based on these analyses and the chamber study, ERI will conduct indoor air monitoring in Florida and Louisiana in three test houses for predetermined parameters. A QAPP is under preparation for the Technical Workgroup to review based on the available information to date, and will be modified based on any new information.

If there are any questions, please call me at 732-321-6761

Sincerely



Raj Singhvi, Chemist

Enclosures

cc: David Krause, FDOH
Barnes Johnson, OSRTI
Arnold Layne, OSRTI/TIFSD
Jeff Heimerman, OSRTI/TIFSD
Dave Wright, ERI
Harry Compton, ERI

Table-1 Results of the Analysis for Metals in Solid Drywall Material, Paper and Paint

Sample No. Sample ID	Method	1		2		3		4		5		6	
		US	China	US	China	MIC/33956-12077	China	US	China	US	China	US	China
%OI at 760C		21	22	21	24			21	24	19	24		
pH of 5% slurry		7.08	7.41	7.28	7.35			7.28	7.35	7.31	7.31		
Analysis		mg/kg	mg/kg	mg/kg	mg/kg			mg/kg	mg/kg	mg/kg	mg/kg		
Aluminum	Modified REAC SOP 1811	305	1180	846	846			846	846	3570	3570		
Barium	Modified REAC SOP 1811	5.14	33.3	42.8	42.8			14.2	14.2	12.8	12.8		
Calcium	Modified REAC SOP 1811	278000	266000	254000	254000			267000	267000	245000	245000		
Chromium	Modified REAC SOP 1811	1.92	5.28	3.68	3.68			2.81	2.81	4.34	4.34		
Cobalt	Modified REAC SOP 1811	<0.87	<0.87	<0.83	<0.83			<0.99	<0.99	2.89	2.89		
Copper	Modified REAC SOP 1811	<1.52	1.78	2.80	2.80			<1.71	<1.71	6.15	6.15		
Iron	Modified REAC SOP 1811	841	3390	1630	1630			1170	1170	3210	3210		
Lead	Modified REAC SOP 1811	<2.17	<2.16	<2.33	<2.33			<2.44	<2.44	3.45	3.45		
Magnesium	Modified REAC SOP 1811	463	6020	10300	10300			934	934	5250	5250		
Manganese	Modified REAC SOP 1832	3.24	48.8	71.3	71.3			16.1	16.1	66.1	66.1		
Mercury	Modified REAC SOP 1811	2.06	0.552	0.190	0.190			0.0868	0.0868	<0.047	<0.047		
Nickel	Modified REAC SOP 1811	<1.30	1.58	1.44	1.44			1.82	1.82	5.41	5.41		
Potassium	Modified REAC SOP 1811	106	368	333	333			135	135	865	865		
Selenium	Modified REAC SOP 1811	8.94	2.81	<3.03	<3.03			3.43	3.43	<2.87	<2.87		
Sodium	Modified REAC SOP 1811	<217	428	488	488			<244	<244	<220	<220		
Vanadium	Modified REAC SOP 1811	<0.87	2.52	2.28	2.28			2.77	2.77	3.36	3.36		
Zinc	Modified REAC SOP 1811	<6.71	<6.71	<7.24	<7.24			<7.56	<7.56	<6.83	<6.83		
Strontium (Drywall/Paper)	Modified REAC SOP 1811	244/45	287/2570	2670/635	2670/635			499/110	499/110	638/19	638/19		
Strontium (Paint)	Modified REAC SOP 1811	NA	280	122	122			NA	NA	NA	NA		
Alkalinity (CaCO3)	SM2320B	<89	<89	970	970			<89	<89	840	840		
Alkalinity - Bicarbonate	SM2320B	<89	<89	970	970			<89	<89	840	840		
Sulfide (Lab 1)	9030B	<4	<4	<4	<4			<4	<4	<4	<4		
Sulfide (Lab 2)	8030B	<10	<10	<10	<10			<10	<10	<10	<10		
Sulfate	Region I, SOP-PC-19	668000	535000	507000	507000			652000	652000	568000	567000		
Chloride (water soluble)	Modified SM 4500-Cl-E	74	250	190	190			38	38	59	59		
Sulfur*	Modified REAC SOP 1805	<8.23	119	83	83			<8.13	<8.13	<7.94	<7.94		
Formaldehyde (Drywall/Paper)	Modified NIOSH 2106	ND/0.58	ND/0.44	ND/ND	ND/ND			ND/0.83	ND/0.83	0.54/ND	0.54/ND		
Total Organic Carbon	Region II SOP-PC-83	4300	2900	4300	4300			2200	2200	5500	5500		
TOTAL ORGANIC COMPOUND* (Drywall/Paper)	REAC SOP 1805	7.7/75	145/125	243/246	243/246			18.3/298	18.3/298	31.5/70	31.5/70		

* GC/MS analysis results from BNA extract including TIC's

Table 2 Qualitative Analysis of Drywall Gypsum- XRF

Sample #	Sample ID	Country	Ca	Fe	Sr
1	US Gypsum/Hamilton	US	222000 +/- 1200	410 +/- 90	180 +/- 10
2	Knauf/33928-20055	China	240000 +/- 1300	720 +/- 110	1970 +/- 32
2(Duplicate)	Knauf/33928-20055	China	241000 +/- 1300	730 +/- 100	1960 +/- 32
3	MIC/33966-12077	China	238000 +/- 1300	930 +/- 120	2130 +/- 34
4	Protec/Certaineed	US	226000 +/- 1200	980 +/- 120	370 +/- 14
5	National Gypsum/Gold Bond	US	210000 +/- 1200	2010 +/- 150	460 +/- 16
6	GP/Tough Rock	US	220000 +/- 1200	1210 +/- 130	844 +/- 21

A. Major - Calcium

Present - Iron, Strontium, Sulfur

Note: the sulfur line appears as weak peak in the XRF spectrum of each sample
(sulfur cannot be quantified in these samples with Niton XRF unit)

B. XRF Results (total concentration) in ppm +/- 1 standard deviation

Table 3 Tentatively Identified Organic Compounds, estimated concentration (mg/kg)

Sample #	1		2		3		4		5		6	
	US Gypsum	Paper	China Gypsum	Paper	MCT13984-12077 China Gypsum	Paper	PROROC(araminked) US Gypsum	Paper	National Gypsum/Gold Bond US Gypsum	Paper	GPR10984 Bost US Gypsum	Paper
Propylene Glycol	3.74											
Ethanol, 2-hydroxy-	0.40											
Hexylene Glycol	6.90								1.67			
2-Propanol, 1-hydroxy-	6.84								1.88			
Ethanol, 2,2'-oxybis-	7.24								0.78			
Hexanoic acid	7.38									1.48		
Ethanol, 2,2'-oxybis-	7.45											
2-Propanol, 1-(2-methoxy-1-methylethoxy)-	7.63											
Ethane, 1,1'-oxybis(2-alkoxy)-	7.86											
2-Propanol, 1-(2-methoxypropoxy)-	8.03											
dipropylene glycol	8.62											
Hexanoic acid, 2-ethyl-	9.40								0.65			
1,3-Pentanediol, 2,2,4-trimethyl-	10.04											
Ethanol, 1-(2-butoxyethoxy)-	10.48											
Unknown	11.11											
Quinoline	11.27											
Unknown	11.45								0.55			
Unknown	11.49											
2-Propanol, 1,1,2-(2-methoxy-1-methylethoxy)-1-methylethoxy-	11.89											
2-Propanol, 1,1,2-(2-methoxy-1-methylethoxy)-1-methylethoxy-	11.98											
2-Propanol, 1,1,2-(2-methoxy-1-methylethoxy)-1-methylethoxy-	11.74											
2-Propanol, 1,1,2-(2-methoxy-1-methylethoxy)-1-methylethoxy-	11.78											
Hexathylene glycol dimethyl ether (7)	11.82											
2-Propanol, 1-(2-methoxy-1-methylethoxy)- isomer	11.96											
Cyclohexanone, dodecamethyl-	11.99											
2,2,4-Triethyl-1,3-pentanediol dibutylate	12.57								0.56			
Propanoic Acid, 2-methyl-2-(2-hydroxy-1-methylethoxy)-1-methylethoxy ester	12.57								1.00			
Propanoic Acid, 2-methyl-2-(2-hydroxy-1-methylethoxy)-1-methylethoxy ester	13.63											
Propanoic Acid, 2-methyl-2-(2-hydroxy-1-methylethoxy)-1-methylethoxy ester	13.83											
Vanillin	13.06											
Cyclohexane	19.75											
Propanoic Acid, 2-methyl-2-(2-hydroxy-1-methylethoxy)-1-methylethoxy ester	14.81								0.88			
Unknown	15.11											
Cedrol	15.47											
Benzyl Benzoate	16.84								1.28			
Homocamphyl sesquiterpene	17.84											
n-Heptanoic acid	18.27											
9-Octadecenoic acid, (E)- or oleic acid	19.72								1.12			
3-(2-Ethylhexyl) malate	19.86								0.19			
Oxobutanoic acid	19.87											
C21 alkane	20.16											
n-alkane	20.69								0.20			
Terpene	21.60								0.65			
propylone, 4-phenyl-	22.26								1.56			
C26 alkane	22.27											
dihydroxydodecane isomer	22.34											
Unknown	22.63								2.76			
C28 alkane	22.81											
C26 alkane	23.31											
C26 alkane	23.54											
Alkene	23.92											
Oxalacetate	24.15											
Alkane	23.99											
Unknown	24.44											
C28 alkane	24.14								0.91			
C28 alkane	24.17											
Alkene	26.28											
Alkene	27.21											
Propylthi sulfone isomer	27.30											
Bisphenyl sulfone isomer	28.19											
Hexafluoroethane	28.30											
C33 n-alkane	29.51											
Tetrafluoroethane	29.80											
Oxidecarboxylic acid, ethyl ester	30.82											
Alkane	30.88											
C35 A ketone	31.13											
1,5-Pentadiene	32.79											
Unknown	32.79											
Total organic	7.55	73.72	142.11	118.61	233.80	49.84	18.31	28.91	30.46	0.89	68.11	35.00